

MATERIAL PERFORMANCE PARAMETERS

DESCRIPTION	UNITS	METHOD	SPECIFICATION	TYPICAL
Basic Weight	g/m ²	ISO 9073-1-1989	±2	60
Machine Direction Strength	N/5cm		≥50	69
Machine Direction Elongation	%		≥100	109
Cross Direction Strength	N/5cm		≥25	43
Cross Direction Elongation	%		≥100	111
Hydrostatic Head	mmH ₂ O	ISO 811-1981	≥100	213
Air Permeability	l/m ² /S	GB/T5453	≥	2000
Surface Resistivity	Ω	ISO 9073-1-1989	/	10 ⁷

HELMKE DRUM TEST RESULT CLASS 1

PARTICLE SIZE	CUMULATIVE RELEASE RATE (COUNTS/MIN)	SPECIFICATION
≥ 0.3µm	743	less than 2,000
≥ 0.5µm	318	2,000 - 20,000

PERMEATION TEST AGAINST CHEMO DRUGS

CHEMOTHERAPY DRUGS	BREAKTHROUGH TIME	TEST METHOD
Carmustine	30 min	ASTM F739-20
Cisplatin	> 480 min	ASTM F739-20
Cyclophosphamide	> 480 min	ASTM F739-20
Doxorubicin HCl	> 480 min	ASTM F739-20
Etoposide	> 480 min	ASTM F739-20
Fluorouracil	> 480 min	ASTM F739-20
Methotrexate	> 480 min	ASTM F739-20
Paclitaxel	> 480 min	ASTM F739-20
Thiotepa	60 min	ASTM F739-20

*Results achieved under controlled laboratory conditions, by accredited ISO 17025 third party testing laboratory

TECHNICAL PROPERTIES

TEST REFERENCE	EXPLANATION	TEST RESULTS	
EN 14325:2004 EN ISO 6530:2005	Repellency to chemicals	10% Sodium Hydroxide	Level 3
		30% Sulphuric Acid	Level 3
		O-Xylene	Level 2
		Butan-1-ol	Level 2
		70% Isopropyl Alcohol	Level 2
		70% Ethanol	Level 2
EN 14325:2004 EN ISO 6530:2005	Resistance to Penetration by chemicals	10% Sodium Hydroxide	Level 3
		30% Sulphuric Acid	Level 3
		O-Xylene	Level 3
		Butan-1-ol	Level 3
		70% Isopropyl Alcohol	Level 3
		70% Ethanol	Level 3
EN 14325:2004 EN ISO 9073-4:1997	Trapezoidal Tear Resistance	Machine Direction	Class 2
		Cross Direction	Class 2
EN 14325:2004 EN ISO 13934-1:2013	Tensile Strength	Machine Direction	Class 1
		Cross Direction	Class 2
EN ISO 13982- 2:2004 EN ISO 13982- 1:2004 (Type 5)	Inward Leakage of aerosols and fine particles into suits	Pass	
	IL _{82/90}	0.765%	
	IL _{8/10}	0.327%	
EN 14325:2004 EN ISO 12947-2:2016	Abrasion Resistance	Class 2	
EN 14325:2004 EN ISO 7854:1997, Method B	Flex Cracking Resistance	Class 6	
EN 14325:2004 EN 863:1995	Puncture Resistance	Class 1	
EN 14325:2004 [5.5]	Seam Strength	Class 2	
EN 13034:2015 + A1:2009 ISO 17491-4:2008	Resistance to penetration by a spray of liquid (Spray Test)	Pass	

LOADING

	EURO-PALLET	STANDARD PALLET
Pallet size	W80 L120cm	W100 L120cm
Gross weight	5.67kg	5.67kg
Carton size	W32 L28 H37cm	W32 L28 H37cm
Nett weight	4.58kg	4.58kg
Air freight pallet	Max height: 139cm Layers: 4 Cartons: 24	Max height: 139cm Layers: 4 Cartons: 32
Sea freight pallet	Max height: 170cm Layers: 5 Cartons: 30	Max height: 170cm Layers: 5 Cartons: 40

DOCUMENTATION



CERTIFICATE OF CONFORMANCE (COC)
CERTIFICATE OF ANALYSIS (COA)
CERTIFICATE OF PROCESSING (COP)

View [sample](#) of COC, COA, COP



FACTORY RELATED CERTIFICATIONS
To request ISO9001 Certificate,
please [email us](#)

Made in Malaysia
HS Code: 6210109000

This data sheet and any other claims made by or on behalf of Isofield shall not be taken as a warranty of merchantability or as a statement that any Isofield products are suitable for a specific purpose. Isofield shall not be held responsible for the end user's choice of product for a particular application.



EUROPE

ISOFIELD (IRELAND) LTD
Charter House, 5 Pembroke Row, Dublin 2
Dublin, D02 FW61, Ireland

ASIA

ISOFIELD SDN BHD
6 Jalan Gudang 16/9, Seksyen 16, 40200, Shah Alam,
Selangor, Malaysia, T +603 5512 1709

CONTACT

www.isofield.com
enquiries@isofield.com