



## PHYSICAL PROPERTIES

THICKNESS, SINGLE WALL	MM*	MILS	TEST METHOD
Finger tip	0.14	5.51	EN 455-2:2015
Palm	0.13	5.11	EN 455-2:2015
Cuff	0.07	2.75	EN 455-2:2015

\* +/- 0.02mm

LENGTH	MIN	TYPICAL	TEST METHOD
From tip of middle finger to edge of cuff	290mm	300mm	EN 21420:2020

STRENGTH PROPERTIES	FORCE AT BREAK	TEST METHOD
Throughout shelf life	≥ 6.0 N	EN 455-2:2015

FREEDOM FROM HOLES	PERFORMANCE	TEST METHOD
Acceptable Quality Level (AQL)	< 1.5 - Level 2 of 3	EN 374-2:2016

## CLEANLINESS PROPERTIES

PARTICLES	TYPICAL PARTICLE COUNT	TEST METHOD
≥ 0.5µm (counts/cm <sup>2</sup> )	< 900	IEST-RP-CC005.4

EXTRACTABLES (ION)	TYPICAL VALUE (µg/cm <sup>2</sup> )	TEST METHOD
Fluoride (F)	ND	IEST-RP-CC005.4
Chloride (Cl)	0.203	IEST-RP-CC005.4
Bromide (Br)	ND	IEST-RP-CC005.4
Nitrate (NO <sub>3</sub> )	0.143	IEST-RP-CC005.4
Phosphate (PO <sub>4</sub> )	0.062	IEST-RP-CC005.4
Sulphate (SO <sub>4</sub> )	0.012	IEST-RP-CC005.4
Sodium (Na)	0.042	IEST-RP-CC005.4
Ammonium (NH <sub>4</sub> )	0.020	IEST-RP-CC005.4
Potassium (K)	0.024	IEST-RP-CC005.4
Calcium (Ca)	0.222	IEST-RP-CC005.4
Magnesium (Mg)	ND	IEST-RP-CC005.4
Zinc (Zn)	ND	IEST-RP-CC005.4

\* ND = Not Detected

## TECHNICAL PROPERTIES

NORM	TEST REFERENCE	EXPLANATION
Chemical innocuousness	EN ISO 21420:2020	Ensures the gloves do not adversely affect the health of the user. The materials present in the gloves must not release substances that are toxic
Sizing & dexterity	EN ISO 21420:2020 and EN ISO 374-2:2019	Determines sizing compliance and glove dexterity
Air leak & water leak	EN ISO 374-2:2019	Assesses the resistance of the glove to penetration
Chemical degradation	EN ISO 374-4:2019	Determines the resistance to degradation by dangerous chemicals
Chemical permeation	EN 16523-1:2015+A1:2018	Determines the resistance of protective glove materials to permeation by potentially hazardous non-gaseous chemicals
Viral penetration	EN 16604:2004	Assesses the resistance of glove materials to penetration by blood-borne pathogens
Endotoxin test	EN 455-3, USP	Specifies requirements for the evaluation of biological safety for gloves
EU type certificate	EN ISO 374-1:2016+A1:2018 Type B EN ISO 374-5:2016 EN ISO 374-4:2019	The applicable essential health and safety requirements of Annex II of the PPE Regulation (EU) 2016/425 as a Category III product
UKCA type certificate	EN ISO 374-1:2016+A1:2018 Type B EN ISO 374-5:2016 EN ISO 374-4:2019	The applicable essential health and safety requirements of PPE Regulation (2016/425) as brought into UK law and amended as a Category III product



## LOADING

	EURO-PALLET	STANDARD PALLET
Pallet size	W80 L120cm	W100 L120cm
Gross weight	6.3 - 8.3kg	6.3 - 8.3kg
Carton size	W28 L32 H30cm	W28 L32 H30cm
Nett weight	4.5 - 6.5kg	4.5 - 6.5kg
Air freight pallet	Max height: 135cm Layers: 4 Cartons: 32	Max height: 135cm Layers: 4 Cartons: 48
Sea freight pallet	Max height: 165cm Layers: 5 Cartons: 40	Max height: 165cm Layers: 5 Cartons: 60

## DOCUMENTATION



CERTIFICATE OF CONFORMANCE (COC)  
CERTIFICATE OF ANALYSIS (COA)

View [sample](#) of COC & COA



DECLARATION OF  
CONFORMITY (DOC)

[Download](#)



FACTORY RELATED CERTIFICATIONS

To request ISO9001 Certificate,  
please [email us](#)

Made in Malaysia  
HS Code: 4015199000

*This data sheet and any other claims made by or on behalf of Isofield shall not be taken as a warranty of merchantability or as a statement that any Isofield products are suitable for a specific purpose. Isofield shall not be held responsible for the end user's choice of product for a particular application.*



### EUROPE

ISOFIELD (IRELAND) LTD  
Charter House, 5 Pembroke Row, Dublin 2  
Dublin, D02 FW61, Ireland

### ASIA

ISOFIELD SDN BHD  
6 Jalan Gudang 16/9, Seksyen 16, 40200, Shah Alam,  
Selangor, Malaysia, T +603 5512 1709

### CONTACT

[www.isofield.com](http://www.isofield.com)  
[enquiries@isofield.com](mailto:enquiries@isofield.com)